


CONFIDENTIAL - Reproduction, publication and dissemination of this publication, enclosures hereto and the information contained therein is prohibited without MAGNETEC's prior written consent.

<b>Client:</b>	<b>MAGNETEC</b>	<b>Magnetec P/N:</b>	<b>M-173</b>		
<b>Client's P/N:</b>	/	<b>PS Index:</b>	<b>03</b>	<b>PS Revision:</b>	<b>08</b>
<b>Subject:</b>	<b>CT Wandler</b>				

1. Mechanical Outline	
Nominal equivalent round core:  <b>19,2 x 15,3 x 5</b>  Finished product dimensions:  OD ≤ 21,4 ID ≥ 13,0 H ≤ 7,3  [dimensions] = mm	

2. Core data (nominal values)			
Core material:	<b>NANOPERM®</b>	$L_{Fe} = 5,40 \text{ cm}$	$A_{Fe} = 0,08 \text{ cm}^2$
Permeability level:	<b>&gt; 90.000</b>	@ frequency <b>80 Hz</b>	@ H peak <b>0,4 mA/cm</b>

3. Inspection values (at room temperature, unless otherwise stated)			
Measured value	Measurement limits	Frequency	leff x N [mA x turn]
<b>AL1 [μH]</b>	<b>11,5 - NA</b>	<b>80 Hz</b>	<b>1,65</b>
<b>AL2 [μH]</b>		<b>80 Hz</b>	<b>30</b>

4. Core finishing	
Type:	<b>Cased</b>
Marking:	<b>MAGNETEC M-173-03 YM (YM = Year/Month), acc. to IEC 60062 6.1.1</b>
Packaging:	<b>75 pcs. per layer; 9 layers per carton box; PU = 675 pcs.</b>

5. Comments
<b>Inspection ratio : 1/AL1[μH]-1/AL2[μH] ≤ 0,0148</b> Visit <a href="http://www.magnetec.de/fileadmin/pdf/pb_ds.pdf">http://www.magnetec.de/fileadmin/pdf/pb_ds.pdf</a> for further information.

Index / Revision	Alteration	Date
02 / 01	ID = 15,3 mm; OD = 19,2 mm	02.04.2002
02 / 02	New annealing program	18.06.2002
02 / 03	New format ; PU = 675 pcs.	28.03.2008
02 / 04	H corrected to ≤ 7,3 mm	27.02.2012
03 / 05	Inductance measurement	12.08.2013
03 / 06	AL measurement	10.10.2013
03 / 07	Case material change	23.08.2018
03 / 08	OD change, inspection ratio correction	11.02.2021

<b>Created:</b>	Z. Palánki 11.02.2021	<b>Approved (Techn):</b>	F. Zámbořský 11.02.2021	<b>Approved (Quality):</b>	Sz. Ilcsik 11.02.2021	<b>Released:</b>	D. Tóth 26.02.2021
-----------------	--------------------------	--------------------------	----------------------------	----------------------------	--------------------------	------------------	-----------------------

CONFIDENTIAL - Reproduction, publication and dissemination of this publication, enclosures hereto and the information contained therein is prohibited without MAGNETEC's prior written consent. Disclosing the specification to third parties or using its content without written permission from MAGNETEC is strictly forbidden and every offender is liable to pay the corresponding damages.