

High inductance and high impedance in a wide frequency range

Advanced EMI suppression over a wide frequency range

Low saturation flux density drop at high temperatures

High saturation current and lower power loss

High operational temperature up to 130°C

MAGNETEC offers advanced and superb EMC-cores based on nanocrystalline NANOPERM® material. Our NANOPERM® material has excellent magnetic properties as its saturation inductance is ca. 1,2T, permeability is adjustable from 1k up to 90k@10kHz, curie temperature is about 600°C and the losses are only 110W/kg@100kHz, 0,3T sin. MAGNETEC have built up a wide standard range of cased cores and offers them with different permeabilities. Our cased cores are encapsulated in a plastic housing with a max temperature about 130°C.

Nom. dim ODxDxH	16x10x6 18,2x7,8x8,4	20x12x8 22,3x10,3x10	25x20x10 27,8x17,5x12,6	25x16x10 28,2x13,2x12,6	30x20x10 32,7x17,8x12,6	40x32x15 43,1x28,8x17,4	40x25x15 44,5x21,4x19	45x30x20 48,5x25,5x24	50x40x20 53,4x36,6x23,5	
μr~ca.1k	M-1601 Isat= 32A	M-1201 Isat=40A	M-1251(c+) Isat=56A	M-659(c+) Isat=50A	M-660(c+) Isat=62A	M-661 Isat=90A	M-1401 Isat=80A	M-1451 Isat=92A	M-1501 Isat=112A	
μr~ca.2k	M-956 Isat=16A	M-1202 Isat=20A	M-1252(c+) Isat=28A	M-669(c+) Isat=25A	M-670(c+) Isat=31A	M-671 Isat=45A	M-1402 Isat=40A	M-796** Isat=46A	M-1502 Isat=56A	
μr~ca. 4k	M-957 Isat=8A	M-1204 Isat=10A	M-1254(c+) Isat=14A	M-679(c+) Isat=12A	M-680(c+) Isat=16A	M-681 Isat=22A	M-934 Isat=16A	M-762 Isat=23A	M-1504 Isat=28A	
μr~ca. 8k	M-709 Isat=4A	M-1208 Isat=5A	M-1258(c+) Isat=7A	M-449(c+) Isat=6A	M-965/ M-450(c+) Isat=8A	M-451 Isat=11A	M-831** Isat=10A	M-1458 Isat=12A	M-951 Isat=14A	
μr~ca. 30k	M-104/ M-125(c++) Isat=1A	M-556 Isat=1A	M-061(c+) Isat=2A	M-062(c+) Isat=1,5A	M-923 Isat=2A	M-994 Isat=3A	M-382 Isat=3A	M-987 Isat=3A	M-967/ M-049 (O) Isat=5A	
μr~ca. 90k	M-940/ M-017(c+)/ M-939(c++) Isat=0,4A	M-059 Isat=0,5A	M-853(c+) Isat=0,6A	M-974(c+) Isat=0,6A	M-845 Isat=0,6A	M-102 Isat=0,7A	M-981 Isat=1A	M-920 Isat=0,9A	M-765 Isat=1A	M-1592 Isat=1,2A

Magnetec GmbH
0049 6184 9202 0
www.magnetec.de
info@magnetec.de

C+: Plastic case with separator holder /C++: Plastic case with base / O: oval shaped versions /***: preliminary /**: almost same size see datasheet

High inductance and high impedance in a wide frequency range

Advanced EMI suppression over a wide frequency range

Low saturation flux density drop at high temperatures

High saturation current and lower power loss

High operational temperature up to 130°C

Definition of Saturation Current I_{sat} of NANOPERM®:

Peak value of the exiting current when the initial inductance level is dropped to 10 per cent. Saturation behavior is very much depending on frequency, signal shape, leakage field, etc. so the mentioned current value is a calculated value for design help only and cannot be guaranteed.

I_{sat} is calculated @ $B = 1,0 \text{ T} / \mu_{nom} / N = 1$.

Nom. dim	50x40x25	63x50x30	80x63x30	100x80x30	130x100x30	160x130x30	200x175x30 236,5x201x30(O)	300x250x30
ODxDxH	53,6x35,9x29,5	68x43x36	85x57x35,5	105x75x35	135x94x34	165x123x34	208x166x37	305x246,5x35
μ_r ~ca.1k	<u>M-1551(c+)</u> Isat=112A	<u>M-662</u> Isat=140A	<u>M-663</u> Isat=180A	<u>M-1801</u> Isat=220A	<u>M-665</u> Isat=290A	<u>M-666</u> Isat=362A	<u>M-667</u> Isat=470A	<u>M-863</u> Isat=688A
μ_r ~ca.2k	<u>M-1552(c+)</u> Isat=56A	<u>M-672</u> Isat=70A	<u>M-673</u> Isat=90A	<u>M-674**/</u> <u>M-1282(O)</u> Isat=111A	<u>M-675</u> Isat=144A	<u>M-676</u> Isat=181A	<u>M-677/</u> <u>M-790(O)</u> Isat=234A	<u>M-873 (O)</u> Isat=344A
μ_r ~ca. 4k	<u>M-1554(c+)</u> Isat=28A	<u>M-682</u> Isat=35A	<u>M-683</u> Isat=45A	<u>M-684**/</u> <u>M-1284(O)</u> Isat=56A	<u>M-685</u> Isat=72A	<u>M-686/</u> <u>M-986(O)</u> Isat=90A	<u>M-687/</u> <u>M-791(O)</u> Isat=117A	<u>M-883(O)</u> Isat=172A
μ_r ~ca. 8k	<u>M-1558(c+)</u> Isat=14A	<u>M-452</u> Isat=18A	<u>M-453</u> Isat=22A	<u>M-954</u> Isat=28A	<u>M-455</u> Isat=36A	<u>M-456/</u> <u>M-792(O)</u> Isat=45A	<u>M-457/</u> <u>M-751(O)</u> Isat=58A	<u>M-582***/</u> <u>M-703(O)</u> Isat=86A
μ_r ~ca. 30k	<u>M-475(c+)</u> Isat=4A	<u>M-112/</u> <u>M-649(O)</u> Isat=5A	<u>M-113/</u> <u>M-283(O)</u> Isat=6A	<u>M-114/</u> <u>M-284(O)</u> Isat=7A	<u>M-115</u> Isat=10A	<u>M-116/</u> <u>M-302(O)</u> Isat=12A	<u>M-117/</u> <u>M-111(O)</u> Isat=16A	<u>M-205/</u> <u>M-248(O)</u> Isat=23A
μ_r ~ca. 60k	<u>M-484(c+)</u> Isat=2A	<u>M-612</u> Isat=2,5A	<u>M-613</u> Isat=3A	<u>M-614</u> <u>M-897(O)</u> Isat=4A	<u>M-615</u> Isat=5A	<u>M-616</u> Isat=6A	<u>M-617</u> Isat=8A	<u>M-618</u> Isat=11A

C+: Plastic case with separator holder /C++: Plastic case with base / O: oval shaped versions /***: preliminary /**: almost same size see datasheet